


## CLAIMS


We claim:

- 5     1.     A strength improvement admixture composition comprising:
- a. polycarboxylate dispersant;
- b. set retarder; and
- c. a strength improvement additive selected from the group consisting of
- 10           poly(hydroxyalkylated)polyethyleneamines,  
         poly(hydroxyalkylated)polyethylenepolyamines,  
         poly(hydroxyalkylated)polyethyleneimines,  
         poly(hydroxyalkylated)polyamines, hydrazines, 1,2-diaminopropane,  
         polyglycoldiamine, poly(hydroxyalkyl)amines and mixtures thereof.
- 15     2.     The admixture composition of claim 1, wherein the amount of polycarboxylate  
         dispersant is from about 5% to about 80%, the set retarder is from about  
         0.5% to about 40%, and the strength improvement additive is from about  
         0.5% to about 40% based on the total dry weight of the admixture  
         composition components.
- 20     3.     The admixture composition of claim 1, wherein the amount of polycarboxylate  
         dispersant is from about 20% to about 60%, the set retarder is from about 2%  
         to about 25%, and the strength improvement additive is from about 2% to  
         about 25% based on the total dry weight of the admixture composition  
25           components.
4.     The admixture composition of claim 1, wherein the strength improvement  
         additive is selected from the group consisting of di(hydroxyethyl)1,2-  
         diaminopropane, tetra(hydroxyethyl)1,2-diaminopropane,  
30           di(hydroxyethyl)hydrazine, tetra(hydroxyethyl)hydrazine, ethoxylated  
         polyglycoldiamine, triisopropanolamine and mixtures thereof.

5. The admixture composition of claim 1, wherein the strength improvement additive is selected from the group consisting of N,N,N'-tri-(hydroxyethyl)ethylenediamine, N,N,N'-tri-(hydroxyethyl)diethylenediamine, N,N'-di-(hydroxyethyl)ethylenediamine, N,N'-bis(2-hydroxypropyl)diethylenetriamine, N,N,N',N'-tetra(hydroxyethyl)ethylenediamine, N,N,N',N',N''-penta(hydroxyethyl)diethylenetriamine, N,N'-bis(2-hydroxypropyl)-N,N,N'-tri(hydroxyethyl)diethylenetriamine, and mixtures thereof.
6. The admixture composition of claim 1, wherein the strength improvement additive comprises poly(hydroxyethyl)polyethyleneimine.
7. The admixture composition of claim 1, wherein the strength improvement additive comprises poly(hydroxyalkylated)polyethyleneamine having the following formula:
- $$\begin{array}{c} (R)_2N[CH_2CH_2N]_xR \\ | \\ R \end{array}$$
- wherein x is 1,2 or 3 and R is selected from the group consisting of hydrogen, 2-hydroxyethyl, and 2-hydroxypropyl, each R can be the same or different, and at least 40% of the R groups are hydroxyalkyl, with no more than 40% of the R groups being hydroxypropyl.
8. The admixture composition of claim 1, wherein the strength improvement additive has the following formula:
- $$(R')_2NCH_2CH_2N(R')_2$$
- wherein R' is  $(CH_2CH_2O)_yH$ , wherein y is 0, 1 or 2, wherein no more than one-half (1/2) of the compounds of the formula have y equal to 0, and each R' can be the same or different.
9. The admixture composition of claim 1, wherein the strength improvement additive has the following formula:




5            wherein R'' is selected from the group consisting of (CH<sub>2</sub>CH<sub>2</sub>O)<sub>y</sub>H and



10

wherein X is a covalent bond or a divalent organic radical selected from the group consisting of CH<sub>2</sub>, CH<sub>2</sub>CH<sub>2</sub>,



15

and CH<sub>2</sub>CH<sub>2</sub>CH<sub>2</sub>OCH<sub>2</sub>CH<sub>2</sub>OCH<sub>2</sub>CH<sub>2</sub>OCH<sub>2</sub>CH<sub>2</sub>CH<sub>2</sub>; wherein y and v are 0, 1


or 2;

20

wherein w is 0 or 1;


wherein v and w cannot both be 0; and wherein no more than one-half (1/2) of the R'' groups are hydrogen.

10.    The admixture composition of claim 1, wherein the strength improvement  
25            additive comprises Ethoxylated Amine HH, having a typical analysis of:



aminoethyl piperazine:	50% to 70% by weight
triethylene tetramine :	40% maximum by weight
others:	balance.

11.    The admixture composition of claim 1, wherein the strength improvement  
30            additive has the following formula:



Wherein R<sup>3</sup> is [(CHR<sup>4</sup>)<sub>m</sub> (CHR<sup>4</sup>)O]<sub>p</sub>H;

wherein  $R^4$  is independently H or  $CH_3$ ;

wherein  $m = 1$  or  $2$ ;

wherein  $n = 2$  or  $3$ ;

wherein  $p = 1$  or  $2$ ;

5 wherein  $q = 3-n$


and each  $R^3$  can be the same or different.

12. The admixture composition of claim 1 wherein the set retarder is selected from the group consisting of an oxy-boron compound, a polyphosphonic acid,  
10 a carboxylic acid, a hydroxycarboxylic acid, polycarboxylic acid, hydroxylated carboxylic acid, fumaric, itaconic, malonic, borax, gluconic, and tartaric acid, lignosulfonates, ascorbic acid, isoascorbic acid, sulphonic acid-acrylic acid copolymer, and their corresponding salts, polyhydroxysilane, polyacrylamide, carbohydrates and mixtures thereof.
- 15 13. The admixture composition of claim 1 further comprising at least one of set accelerators, air detraining agents, air entraining agents, shrinkage reducing admixtures, water reducers, foaming agents, dampproofing admixtures, pumping aids, fungicidal admixtures, insecticidal admixtures, germicidal  
20 admixtures, alkali activity reducers, bonding admixtures, corrosion inhibitors, and pigments.
14. The admixture composition of claim 1, wherein the admixture composition is in an aqueous solution.
- 25 15. A cementitious composition comprising hydraulic cement and a strength improvement admixture composition, said admixture composition comprising:
  - a. polycarboxylate dispersant;
  - b. set retarder; and
  - c. a strength improvement additive selected from the group consisting of a  
30 poly(hydroxyalkylated)polyethyleneamines,  
poly(hydroxyalkylated)polyethylenepolyamines,  
poly(hydroxyalkylated)polyethyleneimines,

poly(hydroxyalkylated)polyamines, hydrazines, 1,2-diaminopropane, polyglycoldiamine, poly(hydroxyalkyl)amines and mixtures thereof.


16. The cementitious composition of claim 15, wherein the amount of polycarboxylate dispersant is from about 0.02% to about 2%, the set retarder is from about 0.002% to about 0.2%, the strength improvement additive is from about 0.0001% to about 0.2% by weight of cementitious binder.
17. The cementitious composition of claim 15, wherein the amount of polycarboxylate dispersant is from about 0.02% to about 0.24%, the set retarder is from about 0.005% to about 0.08%, the strength improvement additive is from about 0.004% to about 0.08% by weight of cementitious binder.
18. The cementitious composition of claim 15, wherein the strength improvement additive is selected from the group consisting of di(hydroxyethyl)1,2-diaminopropane, tetra(hydroxyethyl)1,2-diaminopropane, di(hydroxyethyl)hydrazine, tetra(hydroxyethyl)hydrazine, ethoxylated polyglycoldiamine, triisopropanolamine and mixtures thereof.
19. The cementitious composition of claim 15, wherein the strength improvement additive is selected from the group consisting of N,N,N'-tri-(hydroxyethyl)ethylenediamine, N,N,N'-tri-(hydroxyethyl)diethylenediamine, N,N'-di-(hydroxyethyl)ethylenediamine, N,N'-bis(2-hydroxypropyl)diethylenetriamine, N,N,N',N'-tetra(hydroxyethyl)ethylenediamine, N,N,N',N',N''-penta(hydroxyethyl)diethylenetriamine, N,N'-bis(2-hydroxypropyl)-N,N,N'-tri(hydroxyethyl)diethylenetriamine, and mixtures thereof.
20. The cementitious composition of claim 15, wherein the strength improvement additive comprises poly(hydroxyethyl)polyethyleneimine.

21. The cementitious composition of claim 15, wherein the strength improvement additive comprises poly(hydroxyalkylated)polyethyleneamine having the following formula:



wherein x is 1,2 or 3 and R is selected from the group consisting of hydrogen, 2-hydroxyethyl, and 2-hydroxypropyl, each R can be the same or different, and at least 40% of the R groups are hydroxyalkyl, with no more than 40% of the R groups being hydroxypropyl.


22. The cementitious composition of claim 15, wherein the strength improvement additive has the following formula:



wherein R' is  $(CH_2CH_2O)_yH$ , wherein y is 0, 1 or 2, wherein no more than one-half (1/2) of the compounds of the formula have y equal to 0, and each R' can be the same or different.

20

23. The cementitious composition of claim 15, wherein the strength improvement additive has the following formula:



25


wherein R'' is selected from the group consisting of  $(CH_2CH_2O)_yH$  and



30

wherein X is a covalent bond or a divalent organic radical selected from the group consisting of  $CH_2$ ,  $CH_2CH_2$ ,

35




and  $\text{CH}_2\text{CH}_2\text{CH}_2\text{OCH}_2\text{CH}_2\text{OCH}_2\text{CH}_2\text{OCH}_2\text{CH}_2\text{CH}_2$ ; wherein y and v are 0, 1 or 2;

wherein w is 0 or 1;

5 wherein v and w cannot both be 0; and wherein no more than one-half (1/2) of the R" groups are hydrogen.

24. The cementitious composition of claim 15, wherein the strength improvement additive comprises Ethoxylated Amine HH, having a typical analysis of:


10



aminoethyl piperazine:	50% to 70% by weight
triethylene tetramine :	40% maximum by weight
others:	balance.

25. The admixture composition of claim 15, wherein the strength improvement additive has the following formula:

15



Wherein  $\text{R}^3$  is  $[(\text{CHR}^4)_m (\text{CHR}^4)\text{O}]_p\text{H}$ ;

wherein  $\text{R}^4$  is independently H or  $\text{CH}_3$ ;

wherein  $m = 1$  or  $2$ ;

wherein  $n = 2$  or  $3$ ;

20

wherein  $p = 1$  or  $2$ ;

wherein  $q = 3-n$ ;

and each  $\text{R}^3$  can be the same or different.


25

26. The cementitious composition of claim 15 wherein the set retarder is selected from the group consisting of an oxy-boron compound, a polyphosphonic acid, a carboxylic acid, a hydroxycarboxylic acid, polycarboxylic acid, hydroxylated carboxylic acid, fumaric, itaconic, malonic, borax, gluconic, and tartaric acid, lignosulfonates, ascorbic acid, isoascorbic acid, sulphonic acid-

acrylic acid copolymer, and their corresponding salts, polyhydroxysilane, polyacrylamide, carbohydrates and mixtures thereof.

27. The cementitious composition of claim 15, wherein the cement is selected from the group consisting of portland cement, modified portland cement, or masonry cement, and mixtures thereof.
28. The cementitious composition of claim 15 wherein the hydraulic cement is portland cement.
29. The cementitious composition of claim 15 further comprising a cement admixture or additive that is selected from the group consisting of set accelerator, air detraining agent, air entraining agent, foaming agent, corrosion inhibitor, shrinkage reducing admixture, water reducer, fiber, pigment, pozzolan, clay, strength enhancing agents, rheology modifying agents, water repellents, wetting agents, water soluble polymers, dampproofing admixtures, gas formers, permeability reducers, pumping aids, fungicidal admixtures, germicidal admixtures, insecticidal admixtures, aggregates, alkali- reaction reducers, bonding admixtures, and mixtures thereof.
30. The cementitious composition of claim 29, wherein the aggregate is at least one of silica, quartz, crushed round marble, glass spheres, granite, limestone, calcite, feldspar, alluvial sands, and sand.
31. The cementitious composition of claim 29, wherein the pozzolan is at least one of natural pozzolan, metakaolin, fly ash, silica fume, calcined clay, and blast furnace slag.
32. The composition of claim 1 or 15 wherein the polycarboxylate dispersant comprises at least one of:
  - a) a dispersant of Formula (I):





wherein in Formula (I)

X is at least one of hydrogen, an alkali earth metal ion, an alkaline earth metal ion, ammonium ion, or amine;

5 R is at least one of C<sub>1</sub> to C<sub>6</sub> alkyl(ene) ether or mixtures thereof or C<sub>1</sub> to C<sub>6</sub> alkyl(ene) imine or mixtures thereof;

Q is at least one of oxygen, NH, or sulfur;

p is a number from 1 to about 300 resulting in at least one of a linear side chain or branched side chain;

10 R<sub>1</sub> is at least one of hydrogen, C<sub>1</sub> to C<sub>20</sub> hydrocarbon, or functionalized hydrocarbon containing at least one of -OH, -COOH, an ester or amide derivative of -COOH, sulfonic acid, an ester or amide derivative of sulfonic acid, amine, or epoxy;


15 Y is at least one of hydrogen, an alkali earth metal ion, an alkaline earth metal ion, ammonium ion, amine, a hydrophobic hydrocarbon or polyalkylene oxide moiety that functions as a defoamer;

m, m', m'', n, n', and n'' are each independently 0 or an integer between 1 and about 20;

20 Z is a moiety containing at least one of i) at least one amine and one acid group, ii) two functional groups capable of incorporating into the backbone selected from the group consisting of dianhydrides, dialdehydes, and di-acid-chlorides, or iii) an imide residue; and

25 wherein a, b, c, and d reflect the mole fraction of each unit wherein the sum of a, b, c, and d equal one, wherein a, b, c, and d are each a value greater than or equal to zero and less than one, and at least two of a, b, c, and d are greater than zero;

b) a dispersant of Formula (II):



wherein in Formula (II):

A is COOM or optionally in the “y” structure an acid anhydride group (-CO-O-CO-) is formed in place of the A groups between the carbon atoms to which the A groups are bonded to form an anhydride;

B is COOM

M is hydrogen, a transition metal cation, the residue of a hydrophobic polyalkylene glycol or polysiloxane, an alkali metal ion, an alkaline earth metal ion, ferrous ion, aluminum ion, (alkanol)ammonium ion, or (alkyl)ammonium ion;

R is a C<sub>2-6</sub> alkylene radical;

R<sub>1</sub> is a C<sub>1-20</sub> alkyl, C<sub>6-9</sub> cycloalkyl, or phenyl group;

x, y, and z are a number from 0.01 to 100;

m is a number from 1 to 100; and



n is a number from 10 to 100;

c) a dispersant comprising at least one polymer or a salt thereof having the form of a copolymer of


i) a maleic anhydride half-ester with a compound of the formula RO(AO)<sub>m</sub>H, wherein R is a C<sub>1</sub>-C<sub>20</sub> alkyl group, A is a C<sub>2-4</sub> alkylene group, and m is an integer from 2-16; and

ii) a monomer having the formula CH<sub>2</sub>=CHCH<sub>2</sub>-(OA)<sub>n</sub>OR, wherein n is an integer from 1-90 and R is a C<sub>1-20</sub> alkyl group;

- d) a dispersant obtained by copolymerizing 5 to 98% by weight of an (alkoxy)polyalkylene glycol mono(meth)acrylic ester monomer (a) represented by the following general formula (1):



- 5                    wherein R<sub>1</sub> stands for hydrogen atom or a methyl group, R<sub>2</sub>O for one species or a mixture of two or more species of oxyalkylene group of 2 to 4 carbon atoms, providing two or more species of the mixture may be added either in the form of a block or in a random form, R<sub>3</sub> for a hydrogen atom or an alkyl group of 1 to 5 carbon atoms, and m is a value indicating the average addition mol number of oxyalkylene groups that is an integer in the range of 1 to 100, 95 to 2% by weight of a (meth)acrylic acid monomer (b) represented by the above general formula (2), wherein R<sub>4</sub> and R<sub>5</sub> are each independently a hydrogen atom or a methyl group, and M<sub>1</sub> for a hydrogen atom, a monovalent metal atom, a divalent metal atom, an ammonium group, or an organic amine group, and 0 to 50% by weight of other monomer (c) copolymerizable with these monomers, provided that the total amount of (a), (b), and (c) is 100% by weight;
- 10
- 15
- 20            e) a graft polymer that is a polycarboxylic acid or a salt thereof, having side chains derived from at least one species selected from the group consisting of oligoalkyleneglycols, polyalcohols, polyoxyalkylene amines, and polyalkylene glycols;
- f) a dispersant of Formula (III):



wherein in Formula (III):

D = a component selected from the group consisting of the structure d1, the structure d2, and mixtures thereof;

5 X = H, CH<sub>3</sub>, C<sub>2</sub> to C<sub>6</sub> Alkyl, Phenyl, p-Methyl Phenyl, or Sulfonated Phenyl;

Y = H or -COOM;

R = H or CH<sub>3</sub>;

10 Z = H, -SO<sub>3</sub>M, -PO<sub>3</sub>M, -COOM, -O(CH<sub>2</sub>)<sub>n</sub>OR<sub>3</sub> where n = 2 to 6, -COOR<sub>3</sub>, or -(CH<sub>2</sub>)<sub>n</sub>OR<sub>3</sub> where n = 0 to 6, -CONHR<sub>3</sub>, -CONHC(CH<sub>3</sub>)<sub>2</sub>CH<sub>2</sub>SO<sub>3</sub>M, -COO(CH<sub>2</sub>)<sub>n</sub>OH where n = 2 to 6, or -O(CH<sub>2</sub>)<sub>n</sub>OR<sub>4</sub> wherein n = 2 to 6;

15 R<sub>1</sub>, R<sub>2</sub>, R<sub>3</sub>, R<sub>5</sub> are each independently -(CHRCH<sub>2</sub>O)<sub>m</sub>R<sub>4</sub> random copolymer of oxyethylene units and oxypropylene units where m = 10 to 500 and wherein the amount of oxyethylene in the random copolymer is from about 60% to 100% and the amount of oxypropylene in the random copolymer is from 0% to about 40%;

R<sub>4</sub> = H, Methyl, C<sub>2</sub> to about C<sub>6</sub> Alkyl, or about C<sub>6</sub> to about C<sub>10</sub> aryl;

20 M = H, Alkali Metal, Alkaline Earth Metal, Ammonium, Amine, triethanol amine, Methyl, or C<sub>2</sub> to about C<sub>6</sub> Alkyl;

a = 0 to about 0.8;


b = about 0.2 to about 1.0;

c = 0 to about 0.5;

d = 0 to about 0.5; and

5 wherein a, b, c, and d represent the mole fraction of each unit and the sum of a, b, c, and d is 1.0;

g) a dispersant of Formula (IV):



wherein in Formula (IV):

10 the "b" structure is one of a carboxylic acid monomer, an ethylenically unsaturated monomer, or maleic anhydride wherein an acid anhydride group ( $\text{-CO-O-CO-}$ ) is formed in place of the groups Y and Z between the carbon atoms to which the groups Y and Z are bonded respectively, and the "b" structure must include at least one moiety with a pendant ester linkage and at least one moiety with a pendant amide linkage;

15

X = H,  $\text{CH}_3$ ,  $\text{C}_2$  to  $\text{C}_6$  Alkyl, Phenyl, p-Methyl Phenyl, p-Ethyl Phenyl, Carboxylated Phenyl, or Sulfonated Phenyl;

Y = H,  $\text{-COOM}$ ,  $\text{-COOH}$ , or W;

20 W = a hydrophobic defoamer represented by the formula  $\text{R}_3\text{O}-(\text{CH}_2\text{CH}_2\text{O})_s-(\text{CH}_2\text{C}(\text{CH}_3)\text{HO})_t-(\text{CH}_2\text{CH}_2\text{O})_u$  where s, t, and u are integers from 0 to 200 with the proviso that  $t > (s+u)$  and wherein the total amount of hydrophobic defoamer is present in an amount less than about 10% by weight of the polycarboxylate dispersant;

25 Z = H,  $\text{-COOM}$ ,  $\text{-O}(\text{CH}_2)_n\text{OR}_3$  where  $n = 2$  to 6,  $\text{-COOR}_3$ ,  $\text{-(CH}_2)_n\text{OR}_3$  where  $n = 0$  to 6, or  $\text{-CONHR}_3$ ;

$\text{R}_1$  = H, or  $\text{CH}_3$ ;

$R_2, R_3$ , are each independently a random copolymer of oxyethylene units and oxypropylene units of the general formula  $-(CH(R_1)CH_2O)_mR_4$  where  $m=10$  to  $500$  and wherein the amount of oxyethylene in the random copolymer is from about  $60\%$  to  $100\%$  and the amount of oxypropylene in the random copolymer is from  $0\%$  to about  $40\%$ ;

$R_4 =$  H, Methyl, or  $C_2$  to  $C_8$  Alkyl;

$R_5 =$   $C_1$  to  $C_{18}$  alkyl or  $C_6$  to  $C_{18}$  alkyl aryl;

$M =$  Alkali Metal, Alkaline Earth Metal, Ammonia, Amine, monoethanol amine, diethanol amine, triethanol amine, morpholine, imidazole;


$a =$   $0.01-0.8$ ;

$b =$   $0.2-0.99$ ;


$c =$   $0-0.5$ ; and

wherein  $a, b, c$  represent the mole fraction of each unit and the sum of  $a, b$ , and  $c$ , is  $1$ ;

h) a random copolymer corresponding to the following Formula (V) in free acid or salt form having the following monomer units and numbers of monomer units:



wherein  $A$  is selected from the moieties (i) or (ii)



wherein  $R_1$  and  $R_3$  are selected from substituted benzene,  $C_{1-8}$  alkyl,  $C_{2-8}$  alkenyl,  $C_{2-8}$  alkylcarbonyl,  $C_{1-8}$  alkoxy, carboxyl, hydrogen, and a

ring,  $R_2$  and  $R_4$  are selected from the group consisting of hydrogen and  $C_{1-4}$  alkyl, wherein  $R_1$  and  $R_3$  can together with  $R_2$  and/or  $R_4$  when  $R_2$  and/or  $R_4$  are  $C_{1-4}$  alkyl form the ring;

5  $R_7$ ,  $R_8$ ,  $R_9$ , and  $R_{10}$  are individually selected from the group consisting of hydrogen,  $C_{1-6}$  alkyl, and a  $C_{2-8}$  hydrocarbon chain, wherein  $R_1$  and  $R_3$  together with  $R_7$  and/or  $R_8$ ,  $R_9$ , and  $R_{10}$  form the  $C_{2-8}$  hydrocarbon chain joining the carbon atoms to which they are attached, the hydrocarbon chain optionally having at least one anionic group, wherein the at least one anionic group is optionally sulfonic;

10 M is selected from the group consisting of hydrogen, and the residue of a hydrophobic polyalkylene glycol or a polysiloxane, with the proviso that when A is (ii) and M is the residue of a hydrophobic polyalkylene glycol, M must be different from the group  $-(R_5O)_mR_6$ ;  $R_5$  is a  $C_{2-8}$  alkylene radical;

15  $R_6$  is selected from the group consisting of  $C_{1-20}$  alkyl,  $C_{6-9}$  cycloalkyl and phenyl;

$n$ ,  $x$ , and  $z$  are numbers from 1 to 100;



$y$  is 0 to 100;

$m$  is 2 to 1000;

20 the ratio of  $x$  to  $(y+z)$  is from 1:10 to 10:1 and the ratio of  $y:z$  is from 5:1 to 1:100;

i) a copolymer of oxyalkyleneglycol-alkenyl ethers and unsaturated dicarboxylic acids, comprising:

25 i) 0 to 90 mol % of at least one component of the formula 3a or 3b:



wherein M is a hydrogen atom, a mono- or divalent metal cation, an ammonium ion or an organic amine residue, a is 1, or when M is a divalent metal cation a is  $\frac{1}{2}$ ;


5 wherein X is  $-\text{OM}_a$ ,

$-\text{O}-(\text{C}_m\text{H}_{2m}\text{O})_n-\text{R}^1$  in which  $\text{R}^1$  is a hydrogen atom, an aliphatic hydrocarbon radical containing from 1 to 20 carbon atoms, a cycloaliphatic hydrocarbon radical containing 5 to 8 carbon atoms or an optionally hydroxyl, carboxyl,  $\text{C}_{1-14}$  alkyl, or sulphonic substituted aryl radical containing 6 to 14 carbon atoms, m is 2 to 4, and n is 0 to 100,

$-\text{NHR}_2$ ,  $-\text{N}(\text{R}^2)_2$  or mixtures thereof in which  $\text{R}^2 = \text{R}^1$  or  $-\text{CO}-\text{NH}_2$ ; and

15 wherein Y is an oxygen atom or  $-\text{NR}^2$ ;

ii) 1 to 89 mol% of components of the general formula 4:




wherein  $\text{R}_3$  is a hydrogen atom or an aliphatic hydrocarbon radical containing from 1 to 5 carbon atoms, p is 0 to 3, and  $\text{R}_1$  is hydrogen, an aliphatic hydrocarbon radical containing from 1 to 20 carbon atoms, a cycloaliphatic hydrocarbon radical containing 5 to 8 carbon atoms or an optionally hydroxyl, carboxyl,  $\text{C}_{1-14}$  alkyl, or sulfonic substituted




aryl radical containing 6 to 14 carbon atoms, m is 2 to 4, and n is 0 to 100, and

iii) 0.1 to 10 mol % of at least one component of the formula 5a or 5b:




or




5

wherein S is a hydrogen atom or  $-\text{COOM}_a$  or  $-\text{COOR}_5$ , T is  $-\text{COOR}_5$ ,  
 10  $-\text{W-R}_7$ ,  $-\text{CO}-[\text{-NH-(CH}_2\text{)}_3\text{]-}_s\text{-W-R}_7$ ,  $-\text{CO-O-(CH}_2\text{)}_z\text{-W-R}_7$ , a radical of  
 the general formula:




or  $-(\text{CH}_2)_z\text{-V-(CH}_2)_z\text{-CH=CH-R}_1$ , or when S is  $-\text{COOR}_5$  or  $-\text{COOM}_a$ ,  
 15  $\text{U}_1$  is  $-\text{CO-NHM-}$ ,  $-\text{O-}$  or  $-\text{CH}_2\text{O}$ ,  $\text{U}_2$  is  $-\text{NH-CO-}$ ,  $-\text{O-}$  or  $-\text{OCH}_2$ , V  
 is  $-\text{O-CO-C}_6\text{H}_4\text{-CO-O-}$  or  $-\text{W-}$ , and W is





R<sub>4</sub> is a hydrogen atom or a methyl radical, R<sub>5</sub> is an aliphatic hydrocarbon radical containing 3 to 20 carbon atoms, a cycloaliphatic hydrocarbon radical containing 5 to 8 carbon atoms or an aryl radical containing 6 to 14 carbon atoms, R<sub>6</sub>=R<sub>1</sub> or


5



or

R<sub>7</sub>=R<sub>1</sub> or


or



r is 2 to 100, s is 1 or 2, x is 1 to 150, y is 0 to 15 and z is 0 to 4;

10

iv) 0 to 90 mol % of at least one component of the formula 6a, 6b, or 6c:



5 wherein M is a hydrogen atom, a mono- or divalent metal cation, an ammonium ion or an organic amine residue, a is 1, or when M is a divalent metal cation a is  $\frac{1}{2}$ ;

wherein X is  $\text{---OM}_a$ ,

10  $\text{---O---(C}_m\text{H}_{2m}\text{O)}_n\text{---R}^1$  in which  $\text{R}^1$  is a hydrogen atom, an aliphatic hydrocarbon radical containing from 1 to 20 carbon atoms, a cycloaliphatic hydrocarbon radical containing 5 to 8 carbon atoms or an optionally hydroxyl, carboxyl,  $\text{C}_{1-14}$  alkyl, or sulphonic substituted aryl radical containing 6 to 14 carbon atoms, m is 2 to 4, and n is 0 to 100,

15  $\text{---NH---(C}_m\text{H}_{2m}\text{O)}_n\text{---R}^1$ ,



$\text{---NHR}_2$ ,  $\text{---N(R}^2\text{)}_2$  or mixtures thereof in which  $\text{R}^2 = \text{R}^1$  or  $\text{---CO---NH}_2$ ; and

wherein Y is an oxygen atom or  $\text{---NR}^2$ ;

20

j) a copolymer of dicarboxylic acid derivatives and oxyalkylene glycol-alkenyl ethers, comprising:

i) 1 to 90 mol. % of at least one member selected from the group consisting of structural units of formula 7a and formula 7b:



wherein M is H, a monovalent metal cation, a divalent metal cation, an ammonium ion or an organic amine;

a is  $\frac{1}{2}$  when M is a divalent metal cation or 1 when M is a monovalent metal cation;


wherein  $R^1$  is  $-\text{OM}_a$ , or

$-\text{O}-(\text{C}_m\text{H}_{2m}\text{O})_n-\text{R}^2$  wherein  $R^2$  is H, a  $\text{C}_{1-20}$  aliphatic hydrocarbon, a  $\text{C}_{5-8}$  cycloaliphatic hydrocarbon, or a  $\text{C}_{6-14}$  aryl that is optionally substituted with at least one member selected from the group consisting of  $-\text{COOM}_a$ ,  $-(\text{SO}_3)\text{M}_a$ , and  $-(\text{PO}_3)\text{M}_{a2}$ ;

m is 2 to 4;

n is 1 to 200;

ii) 0.5 to 80 mol. % of the structural units of formula 8:



wherein  $R^3$  is H or a  $\text{C}_{1-5}$  aliphatic hydrocarbon;



p is 0 to 3;

$R^2$  is H, a  $\text{C}_{1-20}$  aliphatic hydrocarbon, a  $\text{C}_{5-8}$  cycloaliphatic hydrocarbon, or a  $\text{C}_{6-14}$  aryl that is optionally substituted with at least one member selected from the group consisting of  $-\text{COOM}_a$ ,  $-(\text{SO}_3)\text{M}_a$ , and  $-(\text{PO}_3)\text{M}_{a2}$ ;

m is 2 to 4;

n is 1 to 200;

iii) 0.5 to 80 mol.% structural units selected from the group consisting of formula 9a and formula 9b:



wherein  $\text{R}^4$  is H,  $\text{C}_{1-20}$  aliphatic hydrocarbon that is optionally substituted with at least one hydroxyl group,  $-(\text{C}_m\text{H}_{2m}\text{O})_n\text{-R}^2$ ,  $-\text{CO-NH-R}^2$ ,  $\text{C}_{5-8}$  cycloaliphatic hydrocarbon, or a  $\text{C}_{6-14}$  aryl that is optionally substituted with at least one member selected from the group consisting of  $-\text{COOM}_a$ ,  $-(\text{SO}_3)\text{M}_a$ , and  $-(\text{PO}_3)\text{M}_{a2}$ ;

M is H, a monovalent metal cation, a divalent metal cation, an ammonium ion or an organic amine;


a is  $\frac{1}{2}$  when M is a divalent metal cation or 1 when M is a monovalent metal cation;

$\text{R}^2$  is H, a  $\text{C}_{1-20}$  aliphatic hydrocarbon, a  $\text{C}_{5-8}$  cycloaliphatic hydrocarbon, or a  $\text{C}_{6-14}$  aryl that is optionally substituted with at least one member selected from the group consisting of  $-\text{COOM}_a$ ,  $-(\text{SO}_3)\text{M}_a$ , and  $-(\text{PO}_3)\text{M}_{a2}$ ;

m is 2 to 4;

n is 1 to 200;

iv) 1 to 90 mol.% of structural units of formula 10



wherein R<sup>5</sup> is methyl, or methylene group, wherein R<sup>5</sup> forms one or more 5 to 8 membered rings with R<sup>7</sup>;

R<sup>6</sup> is H, methyl, or ethyl;

- 5 R<sup>7</sup> is H, a C<sub>1-20</sub> aliphatic hydrocarbon, a C<sub>6-14</sub> aryl that is optionally substituted with at least one member selected from the group consisting of -COOM<sub>a</sub>, -(SO<sub>3</sub>)M<sub>a</sub>, and -(PO<sub>3</sub>)M<sub>a2</sub>, a C<sub>5-8</sub> cycloaliphatic hydrocarbon, -OCOR<sup>4</sup>, -OR<sup>4</sup>, and -COOR<sup>4</sup>, wherein R<sup>4</sup> is H, a C<sub>1-20</sub> aliphatic hydrocarbon that is optionally substituted with at least one -
- 10 OH, -(C<sub>m</sub>H<sub>2m</sub>O)<sub>n</sub>-R<sup>2</sup>, -CO-NH-R<sup>2</sup>, C<sub>5-8</sub> cycloaliphatic hydrocarbon, or a C<sub>6-14</sub> aryl residue that is optionally substituted with a member selected from the group consisting of -COOM<sub>a</sub>, -(SO<sub>3</sub>)M<sub>a</sub>, and -(PO<sub>3</sub>)M<sub>a2</sub>.


- 15 33. A method of making a cementitious composition comprising forming a mixture of water, hydraulic cement and a strength improvement admixture composition, said admixture composition comprising the components of:

- a. polycarboxylate dispersant;
- b. set retarder; and
- 20 c. a strength improvement additive selected from the group consisting of poly(hydroxyalkylated)polyethyleneamines, poly(hydroxyalkylated)polyethylenepolyamines, poly(hydroxyalkylated)polyethyleneimines, poly(hydroxyalkylated)polyamines, hydrazines, 1,2-diaminopropane, polyglycoldiamine, poly(hydroxyalkyl)amines and mixtures thereof.

- 25 34. The method of claim 33, wherein the amount of polycarboxylate dispersant is from about 0.02% to about 2%, the set retarder is from about 0.002% to about 0.2%, the strength improvement additive is from about 0.0001% to about 0.2% by weight of cementitious binder.


35. The method of claim 33, wherein the amount of polycarboxylate dispersant is from about 0.02% to about 0.24%, the set retarder is from about 0.005% to about 0.08%, the strength improvement additive is from about 0.004% to about 0.08% by weight of cementitious binder.
- 5
36. The method of claim 33, wherein the strength improvement additive is selected from the group consisting of di(hydroxyethyl)1,2-diaminopropane, tetra(hydroxyethyl)1,2-diaminopropane, di(hydroxyethyl)hydrazine, tetra(hydroxyethyl)hydrazine, ethoxylated polyglycoldiamine, triisopropanolamine and mixtures thereof.
- 10
37. The method of claim 33, wherein the strength improvement additive is selected from the group consisting of N,N,N'-tri-(hydroxyethyl)ethylenediamine, N,N,N'-tri-(hydroxyethyl)diethylenediamine, N,N'-di-(hydroxyethyl)ethylenediamine, N,N'-bis(2-hydroxypropyl)diethylenetriamine, N,N,N',N'-tetra(hydroxyethyl)ethylenediamine, N,N,N',N',N''-penta(hydroxyethyl)diethylenetriamine, N,N'-bis(2-hydroxypropyl)-N,N,N'-tri(hydroxyethyl)diethylenetriamine, and mixtures thereof.
- 15
38. The method of claim 33, wherein the strength improvement additive comprises poly(hydroxyethyl)polyethyleneimine.
- 20
39. The method of claim 33, wherein the strength improvement additive comprises poly(hydroxyalkylated)polyethyleneamine having the following formula:
- 25
- $$\begin{array}{c} (R)_2N[CH_2CH_2N]_xR \\ | \\ R \end{array}$$
- wherein x is 1,2 or 3 and R is selected from the group consisting of hydrogen, 2-hydroxyethyl, and 2-hydroxypropyl, each R can be the same or different, and at least 40% of the R groups are hydroxyalkyl, with no more than 40% of the R groups being hydroxypropyl.
- 30

40. The method of claim 33, wherein the strength improvement additive has the following formula:




- 5 wherein R' is  $(CH_2CH_2O)_yH$ , wherein y is 0, 1 or 2, wherein no more than one-half (1/2) of the compounds of the formula have y equal to 0, and each R' can be the same or different.

- 10 41. The method of claim 33, wherein the strength improvement additive has the following formula:



- 15 wherein R'' is selected from the group consisting of  $(CH_2CH_2O)_yH$  and



- 20 wherein X is a covalent bond or a divalent organic radical selected from the group consisting of  $CH_2$ ,  $CH_2CH_2$ ,




- and  $CH_2CH_2CH_2OCH_2CH_2OCH_2CH_2OCH_2CH_2CH_2$ ; wherein y and v are 0, 1 or 2;

- 30 wherein w is 0 or 1;  
wherein v and w cannot both be 0; and wherein no more than one-half (1/2) of the R'' groups are hydrogen.

42. The method of claim 33, wherein the strength improvement additive comprises  
35 Ethoxylated Amine HH, having a typical analysis of:






aminoethyl piperazine: 50% to 70% by weight  
 triethylene tetramine : 40% maximum by weight  
 others: balance.

43. The admixture composition of claim 33, wherein the strength improvement additive has the following formula:  
 $(R^3)_n H_q N$
- 5      Wherein  $R^3$  is  $[(CHR^4)_m (CHR^4)O]_p H$ ;  
 wherein  $R^4$  is independently H or  $CH_3$ ;  
 wherein  $m = 1$  or  $2$ ;  
 wherein  $n = 2$  or  $3$ ;  
 wherein  $p = 1$  or  $2$ ;  
 10      wherein  $q = 3-n$ ;  
 and each  $R^3$  can be the same or different.
44. The method of claim 33 wherein the set retarder is selected from the group consisting of an oxy-boron compound, a polyphosphonic acid, a carboxylic acid, a hydroxycarboxylic acid, polycarboxylic acid, hydroxylated carboxylic acid, fumaric, itaconic, malonic, borax, gluconic, and tartaric acid, lignosulfonates, ascorbic acid, isoascorbic acid, sulphonic acid-acrylic acid copolymer, and their corresponding salts, polyhydroxysilane, polyacrylamide, carbohydrates and mixtures thereof.
- 15      20
45. The method of claim 33, wherein the cement is selected from the group consisting of portland cement, modified portland cement, or masonry cement, and mixtures thereof.
46. The method of claim 33 wherein the hydraulic cement is portland cement.
- 25
47. The method of claim 33 further comprising a cement admixture or additive that is selected from the group consisting of set accelerator, air detraining

- agent, air entraining agent, foaming agent, corrosion inhibitor, shrinkage reducing admixture, water reducer, fiber, pigment, pozzolan, clay, strength enhancing agents, rheology modifying agents, water repellents, wetting agents, water soluble polymers, dampproofing admixtures, gas formers, permeability reducers, pumping aids, fungicidal admixtures, germicidal admixtures, insecticidal admixtures, aggregates, alkali- reaction reducers, bonding admixtures, and mixtures thereof.
48. The method of claim 47, wherein the aggregate is at least one of silica, quartz, crushed round marble, glass spheres, granite, limestone, calcite, feldspar, alluvial sands, and sand.
49. The method of claim 47, wherein the pozzolan is at least one of natural pozzolan, metakaolin, fly ash, silica fume, calcined clay, and blast furnace slag.
50. The method of claim 33 wherein the polycarboxylate dispersant comprises at least one of:
- a) a dispersant of Formula (I):



wherein in Formula (I)

- X is at least one of hydrogen, an alkali earth metal ion, an alkaline earth metal ion, ammonium ion, or amine;
- R is at least one of C<sub>1</sub> to C<sub>6</sub> alkyl(ene) ether or mixtures thereof or C<sub>1</sub> to C<sub>6</sub> alkyl(ene) imine or mixtures thereof;

Q is at least one of oxygen, NH, or sulfur;

p is a number from 1 to about 300 resulting in at least one of a linear side chain or branched side chain;

5  $R_1$  is at least one of hydrogen,  $C_1$  to  $C_{20}$  hydrocarbon, or functionalized hydrocarbon containing at least one of  $-OH$ ,  $-COOH$ , an ester or amide derivative of  $-COOH$ , sulfonic acid, an ester or amide derivative of sulfonic acid, amine, or epoxy;


10 Y is at least one of hydrogen, an alkali earth metal ion, an alkaline earth metal ion, ammonium ion, amine, a hydrophobic hydrocarbon or polyalkylene oxide moiety that functions as a defoamer;

m, m', m'', n, n', and n'' are each independently 0 or an integer between 1 and about 20;

15 Z is a moiety containing at least one of i) at least one amine and one acid group, ii) two functional groups capable of incorporating into the backbone selected from the group consisting of dianhydrides, dialdehydes, and di-acid-chlorides, or iii) an imide residue; and

20 wherein a, b, c, and d reflect the mole fraction of each unit wherein the sum of a, b, c, and d equal one, wherein a, b, c, and d are each a value greater than or equal to zero and less than one, and at least two of a, b, c, and d are greater than zero;

b) a dispersant of Formula (II):



wherein in Formula (II):

A is COOM or optionally in the “y” structure an acid anhydride group (-CO-O-CO-) is formed in place of the A groups between the carbon atoms to which the A groups are bonded to form an anhydride;

B is COOM

5 M is hydrogen, a transition metal cation, the residue of a hydrophobic polyalkylene glycol or polysiloxane, an alkali metal ion, an alkaline earth metal ion, ferrous ion, aluminum ion, (alkanol)ammonium ion, or (alkyl)ammonium ion;

R is a C<sub>2-6</sub> alkylene radical;

10 R<sub>1</sub> is a C<sub>1-20</sub> alkyl, C<sub>6-9</sub> cycloalkyl, or phenyl group;

x, y, and z are a number from 0.01 to 100;

m is a number from 1 to 100; and



n is a number from 10 to 100;

15 c) a dispersant comprising at least one polymer or a salt thereof having the form of a copolymer of



i) a maleic anhydride half-ester with a compound of the formula RO(AO)<sub>m</sub>H, wherein R is a C<sub>1</sub>-C<sub>20</sub> alkyl group, A is a C<sub>2-4</sub> alkylene group, and m is an integer from 2-16; and

20 ii) a monomer having the formula CH<sub>2</sub>=CHCH<sub>2</sub>-(OA)<sub>n</sub>OR, wherein n is an integer from 1-90 and R is a C<sub>1-20</sub> alkyl group;

d) a dispersant obtained by copolymerizing 5 to 98% by weight of an (alkoxy)polyalkylene glycol mono(meth)acrylic ester monomer (a) represented by the following general formula (1):



- wherein  $R_1$  stands for hydrogen atom or a methyl group,  $R_2O$  for one species or a mixture of two or more species of oxyalkylene group of 2 to 4 carbon atoms, providing two or more species of the mixture may be added either in the form of a block or in a random form,  $R_3$  for a hydrogen atom or an alkyl group of 1 to 5 carbon atoms, and  $m$  is a value indicating the average addition mol number of oxyalkylene groups that is an integer in the range of 1 to 100, 95 to 2% by weight of a (meth)acrylic acid monomer (b) represented by the above general formula (2), wherein  $R_4$  and  $R_5$  are each independently a hydrogen atom or a methyl group, and  $M_1$  for a hydrogen atom, a monovalent metal atom, a divalent metal atom, an ammonium group, or an organic amine group, and 0 to 50% by weight of other monomer (c) copolymerizable with these monomers, provided that the total amount of (a), (b), and (c) is 100% by weight;
- 15 e) a graft polymer that is a polycarboxylic acid or a salt thereof, having side chains derived from at least one species selected from the group consisting of oligoalkyleneglycols, polyalcohols, polyoxyalkylene amines, and polyalkylene glycols;
- 20 f) a dispersant of Formula (III):



wherein in Formula (III):

D = a component selected from the group consisting of the structure d1, the structure d2, and mixtures thereof;

5 X = H, CH<sub>3</sub>, C<sub>2</sub> to C<sub>6</sub> Alkyl, Phenyl, p-Methyl Phenyl, or Sulfonated Phenyl;

Y = H or -COOM;

R = H or CH<sub>3</sub>;

10 Z = H, -SO<sub>3</sub>M, -PO<sub>3</sub>M, -COOM, -O(CH<sub>2</sub>)<sub>n</sub>OR<sub>3</sub> where n = 2 to 6, -COOR<sub>3</sub>, or -(CH<sub>2</sub>)<sub>n</sub>OR<sub>3</sub> where n = 0 to 6, -CONHR<sub>3</sub>, -CONHC(CH<sub>3</sub>)<sub>2</sub>CH<sub>2</sub>SO<sub>3</sub>M, -COO(CHR<sub>4</sub>)<sub>n</sub>OH where n = 2 to 6, or -O(CH<sub>2</sub>)<sub>n</sub>OR<sub>4</sub> wherein n = 2 to 6;

15 R<sub>1</sub>, R<sub>2</sub>, R<sub>3</sub>, R<sub>5</sub> are each independently -(CHRCH<sub>2</sub>O)<sub>m</sub>R<sub>4</sub> random copolymer of oxyethylene units and oxypropylene units where m = 10 to 500 and wherein the amount of oxyethylene in the random copolymer is from about 60% to 100% and the amount of oxypropylene in the random copolymer is from 0% to about 40%;


R<sub>4</sub> = H, Methyl, C<sub>2</sub> to about C<sub>6</sub> Alkyl, or about C<sub>6</sub> to about C<sub>10</sub> aryl;

20 M = H, Alkali Metal, Alkaline Earth Metal, Ammonium, Amine, triethanol amine, Methyl, or C<sub>2</sub> to about C<sub>6</sub> Alkyl;

- $a =$  0 to about 0.8;  
 $b =$  about 0.2 to about 1.0;  
 $c =$  0 to about 0.5;  
 $d =$  0 to about 0.5; and

5 wherein a, b, c, and d represent the mole fraction of each unit and the sum of a, b, c, and d is 1.0;

g) a dispersant of Formula (IV):



wherein in Formula (IV):

10 the “b” structure is one of a carboxylic acid monomer, an ethylenically unsaturated monomer, or maleic anhydride wherein an acid anhydride group (-CO-O-CO-) is formed in place of the groups Y and Z between the carbon atoms to which the groups Y and Z are bonded respectively, and the “b” structure must include at least one moiety with a pendant ester linkage and at least one moiety with a pendant amide linkage;

X = H, CH<sub>3</sub>, C<sub>2</sub> to C<sub>6</sub> Alkyl, Phenyl, p-Methyl Phenyl, p-Ethyl Phenyl, Carboxylated Phenyl, or Sulfonated Phenyl;

Y = H, -COOM, -COOH, or W;

20 W = a hydrophobic defoamer represented by the formula R<sub>3</sub>O-(CH<sub>2</sub>CH<sub>2</sub>O)<sub>s</sub>-(CH<sub>2</sub>C(CH<sub>3</sub>)HO)<sub>t</sub>-(CH<sub>2</sub>CH<sub>2</sub>O)<sub>u</sub> where s, t, and u are integers from 0 to 200 with the proviso that t > (s+u) and wherein the total amount of hydrophobic defoamer is present in an amount less than about 10% by weight of the polycarboxylate dispersant;

25 Z = H, -COOM, -O(CH<sub>2</sub>)<sub>n</sub>OR<sub>3</sub> where n = 2 to 6, -COOR<sub>3</sub>, -(CH<sub>2</sub>)<sub>n</sub>OR<sub>3</sub> where n = 0 to 6, or -CONHR<sub>3</sub>;

R<sub>1</sub> = H, or CH<sub>3</sub>;

$R_2, R_3$ , are each independently a random copolymer of oxyethylene units and oxypropylene units of the general formula  $-(CH(R_1)CH_2O)_mR_4$  where  $m=10$  to  $500$  and wherein the amount of oxyethylene in the random copolymer is from about  $60\%$  to  $100\%$  and the amount of oxypropylene in the random copolymer is from  $0\%$  to about  $40\%$ ;

$R_4 =$  H, Methyl, or  $C_2$  to  $C_8$  Alkyl;

$R_5 =$   $C_1$  to  $C_{18}$  alkyl or  $C_6$  to  $C_{18}$  alkyl aryl;

$M =$  Alkali Metal, Alkaline Earth Metal, Ammonia, Amine, monoethanol amine, diethanol amine, triethanol amine, morpholine, imidazole;


$a =$   $0.01-0.8$ ;

$b =$   $0.2-0.99$ ;


$c =$   $0-0.5$ ; and

wherein  $a, b, c$  represent the mole fraction of each unit and the sum of  $a, b$ , and  $c$ , is  $1$ ;

h) a random copolymer corresponding to the following Formula (V) in free acid or salt form having the following monomer units and numbers of monomer units:



wherein  $A$  is selected from the moieties (i) or (ii)



wherein  $R_1$  and  $R_3$  are selected from substituted benzene,  $C_{1-8}$  alkyl,  $C_{2-8}$  alkenyl,  $C_{2-8}$  alkylcarbonyl,  $C_{1-8}$  alkoxy, carboxyl, hydrogen, and a



ring,  $R_2$  and  $R_4$  are selected from the group consisting of hydrogen and  $C_{1-4}$  alkyl, wherein  $R_1$  and  $R_3$  can together with  $R_2$  and/or  $R_4$  when  $R_2$  and/or  $R_4$  are  $C_{1-4}$  alkyl form the ring;

5  $R_7$ ,  $R_8$ ,  $R_9$ , and  $R_{10}$  are individually selected from the group consisting of hydrogen,  $C_{1-6}$  alkyl, and a  $C_{2-8}$  hydrocarbon chain, wherein  $R_1$  and  $R_3$  together with  $R_7$  and/or  $R_8$ ,  $R_9$ , and  $R_{10}$  form the  $C_{2-8}$  hydrocarbon chain joining the carbon atoms to which they are attached, the hydrocarbon chain optionally having at least one anionic group, wherein the at least one anionic group is optionally sulfonic;

10  $M$  is selected from the group consisting of hydrogen, and the residue of a hydrophobic polyalkylene glycol or a polysiloxane, with the proviso that when  $A$  is (ii) and  $M$  is the residue of a hydrophobic polyalkylene glycol,  $M$  must be different from the group  $-(R_5O)_mR_6$ ;  $R_5$  is a  $C_{2-8}$  alkylene radical;

15  $R_6$  is selected from the group consisting of  $C_{1-20}$  alkyl,  $C_{6-9}$  cycloalkyl and phenyl;

$n$ ,  $x$ , and  $z$  are numbers from 1 to 100;



$y$  is 0 to 100;

$m$  is 2 to 1000;

20 the ratio of  $x$  to  $(y+z)$  is from 1:10 to 10:1 and the ratio of  $y:z$  is from 5:1 to 1:100;

i) a copolymer of oxyalkyleneglycol-alkenyl ethers and unsaturated dicarboxylic acids, comprising:

25 i) 0 to 90 mol % of at least one component of the formula 3a or 3b:



wherein M is a hydrogen atom, a mono- or divalent metal cation, an ammonium ion or an organic amine residue, a is 1, or when M is a divalent metal cation a is  $\frac{1}{2}$ ;


5 wherein X is  $-\text{OM}_a$ ,

$-\text{O}-(\text{C}_m\text{H}_{2m}\text{O})_n-\text{R}^1$  in which  $\text{R}^1$  is a hydrogen atom, an aliphatic hydrocarbon radical containing from 1 to 20 carbon atoms, a cycloaliphatic hydrocarbon radical containing 5 to 8 carbon atoms or an optionally hydroxyl, carboxyl,  $\text{C}_{1-14}$  alkyl, or sulphonic substituted aryl radical containing 6 to 14 carbon atoms, m is 2 to 4, and n is 0 to 100,

$-\text{NHR}_2$ ,  $-\text{N}(\text{R}^2)_2$  or mixtures thereof in which  $\text{R}^2 = \text{R}^1$  or  $-\text{CO}-\text{NH}_2$ ; and

15 wherein Y is an oxygen atom or  $-\text{NR}^2$ ;


ii) 1 to 89 mol% of components of the general formula 4:




20 wherein  $\text{R}_3$  is a hydrogen atom or an aliphatic hydrocarbon radical containing from 1 to 5 carbon atoms, p is 0 to 3, and  $\text{R}_1$  is hydrogen, an aliphatic hydrocarbon radical containing from 1 to 20 carbon atoms, a cycloaliphatic hydrocarbon radical containing 5 to 8 carbon atoms or an optionally hydroxyl, carboxyl,  $\text{C}_{1-14}$  alkyl, or sulfonic substituted

aryl radical containing 6 to 14 carbon atoms, m is 2 to 4, and n is 0 to 100, and

iii) 0.1 to 10 mol % of at least one component of the formula 5a or 5b:




or




5

wherein S is a hydrogen atom or  $-\text{COOM}_a$  or  $-\text{COOR}_5$ , T is  $-\text{COOR}_5$ ,  
 10  $-\text{W-R}_7$ ,  $-\text{CO-}[-\text{NH}-(\text{CH}_2)_3-]_3-\text{W-R}_7$ ,  $-\text{CO-O}-(\text{CH}_2)_z-\text{W-R}_7$ , a radical of the general formula:




or  $-(\text{CH}_2)_z-\text{V}-(\text{CH}_2)_z-\text{CH}=\text{CH-R}_1$ , or when S is  $-\text{COOR}_5$  or  $-\text{COOM}_a$ ,  
 15  $\text{U}_1$  is  $-\text{CO-NHM-}$ ,  $-\text{O-}$  or  $-\text{CH}_2\text{O}$ ,  $\text{U}_2$  is  $-\text{NH-CO-}$ ,  $-\text{O-}$  or  $-\text{OCH}_2$ , V is  $-\text{O-CO-C}_6\text{H}_4\text{-CO-O-}$  or  $-\text{W-}$ , and W is





R4 is a hydrogen atom or a methyl radical, R5 is an aliphatic hydrocarbon radical containing 3 to 20 carbon atoms, a cycloaliphatic hydrocarbon radical containing 5 to 8 carbon atoms or an aryl radical containing 6 to 14 carbon atoms, R<sub>6</sub>=R<sub>1</sub> or


5



or

R<sub>7</sub>=R<sub>1</sub> or


or



r is 2 to 100, s is 1 or 2, x is 1 to 150, y is 0 to 15 and z is 0 to 4;

10

iv) 0 to 90 mol % of at least one component of the formula 6a, 6b, or 6c:



5 wherein M is a hydrogen atom, a mono- or divalent metal cation, an ammonium ion or an organic amine residue, a is 1, or when M is a divalent metal cation a is  $\frac{1}{2}$ ;

wherein X is  $\text{---OM}_a$ ,

10  $\text{---O---(C}_m\text{H}_{2m}\text{O)}_n\text{---R}^1$  in which  $\text{R}^1$  is a hydrogen atom, an aliphatic hydrocarbon radical containing from 1 to 20 carbon atoms, a cycloaliphatic hydrocarbon radical containing 5 to 8 carbon atoms or an optionally hydroxyl, carboxyl,  $\text{C}_{1-14}$  alkyl, or sulphonic substituted aryl radical containing 6 to 14 carbon atoms, m is 2 to 4, and n is 0 to 100,

15  $\text{---NH---(C}_m\text{H}_{2m}\text{O)}_n\text{---R}^1$ ,



$\text{---NHR}_2$ ,  $\text{---N(R}^2\text{)}_2$  or mixtures thereof in which  $\text{R}^2 = \text{R}^1$  or  $\text{---CO---NH}_2$ ; and

wherein Y is an oxygen atom or  $\text{---NR}^2$ ;

20

j) a copolymer of dicarboxylic acid derivatives and oxyalkylene glycol-alkenyl ethers, comprising:

i) 1 to 90 mol. % of at least one member selected from the group consisting of structural units of formula 7a and formula 7b:



wherein M is H, a monovalent metal cation, a divalent metal cation, an ammonium ion or an organic amine;

a is  $\frac{1}{2}$  when M is a divalent metal cation or 1 when M is a monovalent metal cation;


wherein  $R^1$  is  $-\text{OM}_a$ , or

$-\text{O}-(\text{C}_m\text{H}_{2m}\text{O})_n-\text{R}^2$  wherein  $R^2$  is H, a  $\text{C}_{1-20}$  aliphatic hydrocarbon, a  $\text{C}_{5-8}$  cycloaliphatic hydrocarbon, or a  $\text{C}_{6-14}$  aryl that is optionally substituted with at least one member selected from the group consisting of  $-\text{COOM}_a$ ,  $-(\text{SO}_3)\text{M}_a$ , and  $-(\text{PO}_3)\text{M}_{a2}$ ;

m is 2 to 4;

n is 1 to 200;

ii) 0.5 to 80 mol. % of the structural units of formula 8:



wherein  $R^3$  is H or a  $\text{C}_{1-5}$  aliphatic hydrocarbon;



p is 0 to 3;

$R^2$  is H, a  $\text{C}_{1-20}$  aliphatic hydrocarbon, a  $\text{C}_{5-8}$  cycloaliphatic hydrocarbon, or a  $\text{C}_{6-14}$  aryl that is optionally substituted with at least one member selected from the group consisting of  $-\text{COOM}_a$ ,  $-(\text{SO}_3)\text{M}_a$ , and  $-(\text{PO}_3)\text{M}_{a2}$ ;

m is 2 to 4;

n is 1 to 200;

iii) 0.5 to 80 mol.% structural units selected from the group consisting of formula 9a and formula 9b:



wherein  $\text{R}^4$  is H,  $\text{C}_{1-20}$  aliphatic hydrocarbon that is optionally substituted with at least one hydroxyl group,  $-(\text{C}_m\text{H}_{2m}\text{O})_n\text{-R}^2$ ,  $-\text{CO-NH-R}^2$ ,  $\text{C}_{5-8}$  cycloaliphatic hydrocarbon, or a  $\text{C}_{6-14}$  aryl that is optionally substituted with at least one member selected from the group consisting of  $-\text{COOM}_a$ ,  $-(\text{SO}_3)\text{M}_a$ , and  $-(\text{PO}_3)\text{M}_{a2}$ ;

M is H, a monovalent metal cation, a divalent metal cation, an ammonium ion or an organic amine;


a is  $\frac{1}{2}$  when M is a divalent metal cation or 1 when M is a monovalent metal cation;

$\text{R}^2$  is H, a  $\text{C}_{1-20}$  aliphatic hydrocarbon, a  $\text{C}_{5-8}$  cycloaliphatic hydrocarbon, or a  $\text{C}_{6-14}$  aryl that is optionally substituted with at least one member selected from the group consisting of  $-\text{COOM}_a$ ,  $-(\text{SO}_3)\text{M}_a$ , and  $-(\text{PO}_3)\text{M}_{a2}$ ;

m is 2 to 4;

n is 1 to 200;

iv) 1 to 90 mol.% of structural units of formula 10



wherein R<sup>5</sup> is methyl, or methylene group, wherein R<sup>5</sup> forms one or more 5 to 8 membered rings with R<sup>7</sup>;

R<sup>6</sup> is H, methyl, or ethyl;

5 R<sup>7</sup> is H, a C<sub>1-20</sub> aliphatic hydrocarbon, a C<sub>6-14</sub> aryl that is optionally substituted with at least one member selected from the group consisting of -COOM<sub>a</sub>, -(SO<sub>3</sub>)M<sub>a</sub>, and -(PO<sub>3</sub>)M<sub>a2</sub>, a C<sub>5-8</sub> cycloaliphatic hydrocarbon, -OCOR<sup>4</sup>, -OR<sup>4</sup>, and -COOR<sup>4</sup>, wherein R<sup>4</sup> is H, a C<sub>1-20</sub> aliphatic hydrocarbon that is optionally substituted with at least one -

10 OH, -(C<sub>m</sub>H<sub>2m</sub>O)<sub>n</sub>-R<sup>2</sup>, -CO-NH-R<sup>2</sup>, C<sub>5-8</sub> cycloaliphatic hydrocarbon, or a C<sub>6-14</sub> aryl residue that is optionally substituted with a member selected from the group consisting of -COOM<sub>a</sub>, -(SO<sub>3</sub>)M<sub>a</sub>, and -(PO<sub>3</sub>)M<sub>a2</sub>.

15